

BESKRIVNING

| | | | |
|--------------------|--------------|--------|-----------------|
| Total tjocklek | EN ISO 24346 | mm | 2.90 |
| Tjocklek slitskikt | EN ISO 24340 | mm | 0.30 |
| Vikt | EN ISO 23997 | g/sq.m | 1740 |
| Bredd | EN ISO 24341 | cm | 200 / 300 / 400 |
| Längd | EN ISO 24341 | lm | 25 |

KLASSIFICERING

| | | | |
|-----------------------|--------------|-------|---------------------|
| Produktspecifikation | - | - | EN ISO 26986 |
| Bruksklass | EN ISO 10874 | klass | 23 - 31 |
| Brandklassificering | EN 13 501-1 | klass | C _{fl} -S1 |
| Elektrisk uppladdning | EN 1815 | kV | < 2 |






TESTVÄRDEN

| | | | |
|-----------------------|-----------------|-----------------|--------|
| Avnötning | EN 660.2 | mm ³ | < 2.0 |
| Slitklass | - | grupp | T |
| Dimenssionsstabilitet | EN ISO 23999 | % | ≤ 0.40 |
| Intrycksbeständighet | EN ISO 24343-1 | mm | ≤ 0.25 |
| Ljudisolering | EN ISO 717-2 | dB | 20 |
| Rullande stolshjul | ISO 4918 | - | OK |
| Termiska egenskaper | EN ISO 10456 | W/(m.K) | 0.25 |
| Ljusbeständighet | EN 20 105 - B02 | grader | ≥ 6 |
| Ytbehandling | - | - | PUR+ |
| Kemikaliebeständighet | EN ISO 26987 | - | OK |

MILJÖ / LUFTKVALITET INOMHUS

| | | | |
|---------------------|-------------|-------------------|-------|
| TVOC efter 28 dagar | ISO 16000-6 | µg/m ³ | < 100 |
|---------------------|-------------|-------------------|-------|

CE MÄRKNING

| | | |
|--|-----------------|--|
|  | <p>EN 14041</p> |    |
| | |  |